

Dawnprene TPV 2173A

TPV

TPV

Features:

A soft, natural thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties, chemical resistance and elasticity, designed for extrusion and injection applications. This grade of TPV can be processed on conventional thermoplastics equipment for extrusion, injection molding. It is polyolefin based and completely recyclable.

RoHS	RoHS		
	2019-5-16		
	0.917	g/cm ³	ASTM D792
70 *24 7KPA		—	—
(Shore A, 10 sec, 23)	72.3	A	ASTM D2240
100% - 23	3.13	Mpa	ASTM D412
- 23	7.31	Mpa	ASTM D412
- 23	570	%	ASTM D412
- 23 Die C	33.2	KN/m	ASTM D624
			ASTM D395
23 , 70hr, 1 B	33	%	
70 , 22hr, 1 B	38	%	
100 , 22hr, 1 B	58	%	
	-55		ASTM D746
	-40 105		
	-60 125		
(23)	2.65		ASTM D150
	35	mm/min	GB/T8410
(125 , 168hr)	-12	%	ASTM D573
(125 , 168hr)	-18	%	
(125 , 168hr)	-2	A	
(125 , 168hr)	-1.5	%	

200PPHM 40 *72			ASTM D7762
----------------	--	--	------------

0.01%

Drying Instructions: Need drying the granules before make molding,excessive moisture will lead materials bad extrusion surface,mechanical performance reduction and bad surface appearance. Moisture content request below 0.01%,suggesting drying as follow process:

Drying conditions	Dring temperature/	Dring time/h
first choice	80 90	2 3
other choice	100	1

110

105

If drying temperature over than 110 ,it might cause materials blocking in barrel zone;if use moisture analysis meter,the temperture setting should be on 105 .

R							
40-150	160-170	180-185	190-210	190-215	180-205	170-185	50-70

1.Dawnprene TPV PVC

Dawnprene TPV is incompatible with PVC mateials,hence must clean the equipment before using.