

Dawnflex TPU DN-1095-T2

General information			
Material Properties	Good formability, high transparency, easy to post-processing		
Application Market	Electronic protection cover, shoes, pipes, casters, modified, cables		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.22	g/cm ³	ASTM D792
Shore Hardness	95± 1	A	ASTM D2240
Tensile Strength	36	MPa	ASTM D412
100% Modulus	12	MPa	ASTM D412
300% Modulus	18	MPa	ASTM D412
Elongation at Break	500	%	ASTM D412
Tear Strength	130	KN/m	ASTM D624
Processing suggestions			
Processing conditions			
Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%, suggesting drying as follow process:			
Drying conditions	Drying temperature/		Drying time/h
	90-100		2-4
Processing temperature			
Injection	Set Value	Extrusion	Set Value
Nozzle	215-225	Nozzle	200-210
Front Barrel	210-220	Front Barrel	195-205
Middle Barrel	210-220	Middle Barrel	190-200
Rear Barrel	205-215	Rear Barrel	190-200
Healthy Safety Environmental: Take SDS for reference			
Extra information			
1.The above properties are typical performance which is not regarding as technical index or agreement.			
2.Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.			
SHANDONG DAWN POLYMER Co., Ltd.			
Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703			
Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988			