

Dawnflex TPU DN-2595-T1

25kg/			
	1.22	g/cm ³	ASTM D792
	95± 2	A	ASTM D2240
	40	MPa	ASTM D412
100%	12	MPa	ASTM D412
300%	20	MPa	ASTM D412
	500	%	ASTM D412
	140	KN/m	ASTM D624
100	0.05%		
100			
	/	/h	
	90-100	2-4	
	220-230		190-200
	215-220		190-200
	210-215		185-195
	210-215		180-190
SDS			
1.			
2.			
:	. 265703		
() 0086-535-8868588;	()0086-535-8833988

Dawnflex TPU DN-2595-T1

General information			
Material Properties	High transparency, low precipitation risk, easy to post-processing		
Application Market	Shoes, pipes, modified, cables		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.22	g/cm ³	ASTM D792
Shore Hardness	95± 2	A	ASTM D2240
Tensile Strength	40	MPa	ASTM D412
100% Modulus	12	MPa	ASTM D412
300% Modulus	20	MPa	ASTM D412
Elongation at Break	500	%	ASTM D412
Tear Strength	140	KN/m	ASTM D624
Processing suggestions			

Processing